

## PARAFFIN WAX

Paraffin Wax Grade	Oil Content %wt max.	Melting Point °c	Color min SUS	Penetration 0.1mm@25°C	Viscosity@ 100°C(cSt)
	ASTM, D-721	ASTM, D-87	Saybolt	ASTM, D-1321	ASTM, D-445
L1	1	60-62	28	18-23	3.6-4.4
L2	2	58-60	28	15-19	3.6-4.4
L3	3	58-61	28	18-23	3.6-4.4
L5	5	55-60	-	18-23	3.6-4.4
L10	10	54-59	-	18-23	3.6-4.4
M1	1	62-66	28	15-19	4.5-6.4
M2	2	62-65	28	15-19	4.5-6.4
M3	3	61-65	28	15-19	4.5-6.4
M5	5	60-65	20	15-19	4.5-6.4
M10	10	60-65	-	15-19	4.5-6.4
MB1	1	64-66	25	Max 19	4.5-6.4
MB2	2	63-65	25	Max 19	4.5-6.4
H1	1	68-71	22	Max 21	6.5-8.0
H2	2	68-71	22	Max 23	6.5-8.0
H3	3	67-69	18	Max 23	6.5-8.0
H5	5	67-69	-	Max 23	6.5-8.0
H10	10	66-69	-	-	6.5-8.0