BITUMEN 60/70 SPECIFICATION

Items	Value	Test Method
Density at 25°C, gr/cm3	1.01-1.06	ASTM D-70
Penetration @ 25°C , 0.1mm	60-70	ASTM D-5
Softening Point(R&B) °C	46 min	ASTM D-36
Ductility @ 25°C , 5cm/min,cm	100 min	ASTM D-113
Loss on heating (%WT)	0.2 max	ASTM D-6
Drop in Penetration after heating (%)	20 max	ASTM D-6&D-5
Flash Point (°C)	250 min	ASTM D-92
Solubility in TCE (%WT)	99.5 min	ASTM D-2042
Spot Test	negative	A.A.S.H.O.T.102*

*American Association of state highway officials.

BARUS