

Bitumen MC30

HS CODE: 27132010

CAS No.: 8052-42-4


PACKING

BITUMEN MC 30

Characteristic	Value	Test Method
Kinematic Viscosity@ 60 °C (cSt)	30-60	ASTM D-2170
Flash Point (top open cup) (°C)	38 min	ASTM D-3143
Water Content (%vol)	0.2 max	ASTM D-95
Distillate, %volume of total distillate to @ 360 °C:		
to 225 °C	25 max	ASTM D-402
to 260 °C	40-70	ASTM D-402
to 316 °C	75-93	ASTM D-402
Residue from Distillation to 360 °C (%Vol by difference)	50min	—
Test on Residue from Distillation		
Penetration @ 25 °C (dmm)	120-250	ASTM D-5
Ductility @ 25 °C (cm)	100 min	ASTM D-113
Solubility in Trichloroethylene (%wt)	99 min	ASTM D-2042
*American Association of State Highway Officials		

Packing Details

Specification	Normal Drum	Normal Drum
	180KG	150KG
Height (mm)±5	980	860
Diameter (mm)±5	500	500
Net Weight (KG) ±3.5	182	150
Gross Weight (KG) ±4.5	192	158
Empty Drum Weight (KG) ±1	9.5	8.5



ISO 10002:2018



ISO 10004:2018



ISO 9001:2015

