

Bitumen 35/50

HS CODE: 27132010

CAS No.: 8052-42-4


PACKING

BITUMEN 35/50 SPECIFICATION

Items	Test Method	Unit	Result
Penetration@25°C	IP49	Mm/10	35.5
Softening Point	IP 58	°C	50.58
Resistance to hardening at 163°C			
Change of mass	-	%	0.5
Retained Penetration	IP49	%	53 min
Softening Point after hardening	IP58	°C	52
Flash Point	IP36	°C	240 min
solubility	IP47	Wt%	99 min
Kinematic Viscosity @135°C	IP 370	Mm2/s	400 min

Packing Details

Specification	Normal Drum 180KG	Normal Drum 150KG
Height (mm)±5	980	860
Diameter (mm)±5	500	500
Net Weight (KG) ±3.5	182	150
Gross Weight (KG) ±4.5	192	158
Empty Drum Weight (KG) ±1	9.5	8.5



ISO 10002:2018



ISO 10004:2018



ISO 9001:2015

