

PVC RESIN

TYPE	S-57	S-60	S-65	S-67	S-70
Appearance	W.P.*	W.P.	W.P.	W.P.	W.P.
Inherent Viscosity	0.67 - 0.72	0.74 - 0.79	0.85 - 0.91	0.91 - 0.95	0.98 - 1.02
K-Value	56 - 58	59 - 61	64 - 66	66 - 68	69 - 71
Particle size %Retained on 40 Mesh %Retained on 200 Mesh	Nil => 85	Nil => 85	Nil => 85	Nil => 85	Nil => 85
Porosity [ML/GR]	0.05 - 0.2	0.05 - 0.22	0.1 - 0.26	0.12 - 0.28	0.2 - 0.32
Volatite Matter [Heart Loss] %Max	0.7	0.7	0.7	0.7	0.7
Bulk Density [GR/CC] [Apparent]	0.5 - 0.62	0.55 - 0.61	0.46 - 0.60	0.45 - 0.57	0.44 - 0.5
Dark Resin [Per 10 SQ.IN.]	0 - 10	0 - 10	0 - 10		0 - 10